

COLORPRINT® EXTRA

BECIFICATIONS

*•	Average Thickness	Q	♀
Composition		Carrier	Certifications
PVC	150 microns	non adhesive polyester	REACH n° 1907/2006/EU

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
nylon, polyester, treated fabrics,	▲ Blade	Pressure	» Speed	© Time	Lemperature	<u>∽</u> Pressure	el Peel
leather	45°	70 gf	20 cm/sec	15 seconds	165°C (329°F)	Medium (2,5/3,5 bar)	hot

- → Print, cut and peel off excess material
- \rightarrow Remove the print from the carrier with the help of TTD Easy
- ightarrow Place the decoration on the fabric
- → Apply following the recommended parameters
- → Remove the substrate hot

PRODUCT HIGHLIGHTS

- → Bright colors
- → Applicable on difficult fabrics (nylon, non-woven, leather)

🗹 NOTE: Given the large number of inks and printers, we highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

₩ Washing	A Ironing	🖸 Tumble dry	O Dry cleaning	C Storage Shelf Life	C Storage Temperature	Conditions	ا ⊳ Position
Up to 40°C, best inside- out	NO	NO	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

 \rightarrow Wait 24 hours after the application before the first wash

- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246

