

EASYSUBLI®

SPECIFICATIONS

Composition	र्मे Average Thickness	Carrier				
	220 microns	non adhesive polyester	REACH n° 1907/2006/EU			
PU			OEKO-TEX ® CONFIDENCE IN TEXTILES STANDARD 100 18.HIT.40906 HOHENSTEIN HTTI			

APPLICATION INSTRUCTIONS

⊘ Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
	45°	120 gf	20 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	hot

- → Print, cut, and weed material
- → Remove the print from the carrier by hand and place it on the garment
- → Cover the print with silicon or parchment paper
- → Heat apply at the conditions shown above
- \Rightarrow *TTD Special application tape is required when designs have multiple pieces that need to be kept in alignment. Peel it hot

PRODUCT HIGHLIGHTS

- > receptive to sublimation inks
- → quick application time + low temperature
- → vibrant colors
- → For applications on Cotton and Dark Fabrics
- NOTE: Given the large number of sublimation inks and printers, we highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ ⊳ Position
Up to 60°C, inside-out	YES best inside-out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- \rightarrow Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



